

Biodegradable*
Recycled Content

Panel | Acoustic

Purpose 1302

Purpose 1302

CLEAN IMPACT **TEXTILES**[®]

Specifications

Content	100% post-consumer recycled biodegradable* polyester
Weight	14.1 ± 1.0 oz./lin. yd 250 g/m ² (± 5%)
Width	67" min. useable 168 cm min. useable
Repeat	none
Tackable	yes

Performance

 Colorfastness to light (AATCC 16.3 Option 3) Grade 4 min. at 40 hours
 Colorfastness to crocking (AATCC 8) Grade 4 min. dry & Grade 3 min. wet
 Breaking Strength (ASTM D5034) 205 lbf min. warp and 215 lbf min. fill
 Flammability ASTM E84 Class I or A

Cleaning Code

Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup. May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners.

Acoustical Performance

Our acoustic fabrics are all acoustically transparent. This represents the amount of sound that passes through the fabric.

Acoustic Transparency:	95%
------------------------	-----

For more detailed results, please consult our website.

Miscellaneous

- Application testing of this product is recommended.
- Colors may vary between dye lots.
- This is a directional fabric.
- Tackable properties may vary depending on fabric structure and recovery characteristics.

Proudly woven in North America supporting our local communities.

 [®] This pattern is included in the underwriters laboratory panel fabric recognition program. Additional testing of this U.L. recognized fabric is not required on approved panels from participating manufacturers.

*Certification Marks owned by the Association for Contract Textiles, Inc.

Sustainability

BIODEGRADABLE* CLEAN IMPACT TEXTILES[®]
address the daunting problem of how to deal with polyester fabric at the end of its useful life.

Biodegradable* in landfill after 1,278 days (tested under ASTM D5511)

*Rate and extent of biodegradation into elements found in nature is 91% after 1,278 days under ASTM D5511 (Anaerobic Biodegradation of Plastic Materials Under High Solids Anaerobic Digestion Conditions). The test was done with the same component (PET) polyester and biocatalyst additive. No evidence of further degradation.

duvaltex

USA & INTERNATIONAL | T 800-544-0200
CANADA | T 418 227-9897
For samples, visit **duvaltex.com**



FC-1302 26/08

CLEAN IMPACT **TEXTILES**[®]