

Recycled Content

Panel | Acoustic

Anchorage 2335

White† 2664	Drift 8570	Pearl 8573	Shell 8572	Dune 8583	North Star 8578	Dew 8579	Foam 8585	Fog 8586	Overcast 8575
Vanilla 2130	Birch 2129	Angora 2035	Goose 2049	Cumin 2050	Shadow 6694	Breeze 8582	Slate 2017	Wolf 2027	Asteroid 2053
Lemon 2839	Sunshine 2082	Straw 2034	Goldenrod 2090	Pumpkin 2021	Eucalyptus 2047	Green Apple 2087	Willow 2028	Fern 2840	Pine Needle 2022
Geranium 2084	Poppy 2091	Red Delicious 2014	Mulberry 2044	Orchid 2843	Quarry Blue 2026	Bay 8703	Waterfall 2691	Turquoise 2841	Deep Water 2051
Fossil 2093	Graphite 2079	Coffee Bean 2083	Aubergine 2036	Onyx 2016	Pool 2842	Lapis 2094	Thistle 2085	Cobalt 2045	Midnight 2025

† Suitable for printing

Specifications

Content	100% post-consumer recycled polyester
Weight	15.2 ± 1.0 oz./lin. yd 277 g/m ² (± 5%)
Width	66" min. useable 168 cm min. useable
Repeat	none
Tackable	yes

Cleaning Code

Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup. May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners.

Miscellaneous

- Application testing of this product is recommended.
- Colors may vary between dye lots.
- Dye lots may vary.
- Tackable properties may vary depending on fabric structure and recovery characteristics.

Sustainability

100% recycled and recyclable



Renowned for its exceptional performance and style, Guilford of Maine has set industry standards in acoustics and panel fabrics for many decades. We present the Guilford of Maine Collection - a selection of timeless fabrics.

Performance


	Colorfastness to light (AATCC 16.3 Option 3) Grade 4 min. at 40 hours
	Colorfastness to crocking (AATCC 8) Grade 4 min. dry & Grade 3 min. wet
	Breaking Strength (ASTM D5034) 275 lbf min. warp and fill
	Flammability ASTM E84 Class I or A CAN/ULC-S102.2 EN 1021-1 Cigarette EN 1021-2 Match EN 13501-1 Adhered Class B, s1, d0 Flammability performance may vary depending on the substrate used.
	Abrasion (ASTM D4157) * Wyzenbeek Abrasion Resistance (ASTM D4157) 100,000 double rubs min. cotton duck Martindale Abrasion Resistance (ISO 12947-2) 100,000 cycles

Acoustical Performance

Our acoustic fabrics are all acoustically transparent. This represents the amount of sound that passes through the fabric.

Acoustic Transparency:	85%
------------------------	-----

For more detailed results, please consult our website.



*Multiple factors affect fabric durability and appearance retention, including end-user application and proper maintenance. Wyzenbeek results above 100,000 double rubs have not been shown to be an indicator of increased lifespan.

Certification Marks owned by the Association for Contract Textiles, Inc.

