

Ocean Waste
Biodegradable*

Seating | Panel | Acoustic

Gather 2195

Halo 422	Haze 430	Breeze 426	Pearl 411
Peacan 412	Cornflower 429	Storm 425	Mineral Rock 415
Rustic 420	Dusk 428	Twilight 427	Anchor 416
Sedona 421	Plum Grey 413	Bottle Green 424	Anthracite 417
Cherry Lacquer 419	Truffle 414	Laurel 423	Onyx 418

CLEAN IMPACT TEXTILES®

Gather 2195

CLEAN IMPACT TEXTILES®

Specifications

Content	82% post-consumer recycled biodegradable* polyester including ocean waste 18% biodegradable* polyester
Weight	16.4 ± 1.0 oz./lin. yd 371 g/m² (± 5%)
Width	54" min. useable 137 cm min. useable
Repeat	none

Cleaning Code

Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup. May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners.

Miscellaneous

- Application testing of this product is recommended.
- Colors may vary between dye lots.
- This is a directional fabric.

Sustainability

OCEAN WASTE CLEAN IMPACT TEXTILES®
For every pound of fabric produced, up to half a pound of marine waste is removed from the ocean.

SEAQUAL INITIATIVE

By partnering with the SEAQUAL INITIATIVE, we transform ocean waste into amazing textiles.

BIODEGRADABLE* CLEAN IMPACT TEXTILES®
address the daunting problem of how to deal with polyester fabric at the end of its useful life.

Biodegradable* in landfill after 1,278 days (tested under ASTM D5511)

*Rate and extent of biodegradation into elements found in nature is 91% after 1,278 days under ASTM D5511 (Anaerobic Biodegradation of Plastic Materials Under High Solids Anaerobic Digestion Conditions). The test was done with the same component (PET) polyester and biocatalyst additive. No evidence of further degradation.

Duvaltex is an official and authorized advertiser of SEAQUAL® YARN, the SEAQUAL INITIATIVE and their related trademarks, under licence agreement. Only SEAQUAL licensees are permitted to publicly advertise details about SEAQUAL trademarks.

duvaltex

USA & INTERNATIONAL | T 800-544-0200
CANADA | T 418 227-9897
For samples, visit duvaltex.com

Performance

	Colorfastness to light (AATCC 16.3 Option 3) Grade 4 min. at 40 hours
	Colorfastness to crocking (AATCC 8) Grade 4 min. dry & Grade 4 min. wet
	Breaking Strength (ASTM D5034) 373 lbf min. warp and 328 lbf min. fill
	Seam Slippage (ASTM D4034) 115 lbf min. warp and 103 lbf min. fill
	Pilling Resistance (ASTM D3511) Class 4 min.
	Flammability CA Technical Bulletin 117-2013 Section 1 NFPA 260-2013 Class I ASTM E84 Class I or A EN 1021-1 Cigarette EN 1021-2 Match EN 13501-1 Adhered Class B, s1, d0 Flammability performance may vary depending on the substrate used.
	Abrasion (ASTM D4157) * Wyzenbeek Abrasion Resistance (ASTM D4157) 100,000 double rubs min. cotton duck Martindale Abrasion Resistance (ISO 12947-2) 65,000 cycles

Acoustical Performance

Our acoustic fabrics are all acoustically transparent. This represents the amount of sound that passes through the fabric.

Acoustic Transparency:	90%
------------------------	-----

For more detailed results, please consult our website.

 This pattern is included in the underwriters laboratory panel fabric recognition program. Additional testing of this U.L. recognized fabric is not required on approved panels from participating manufacturers.

*Certification Marks owned by the Association for Contract Textiles, Inc.

