

C0 Stain Repellent

Seating

Frolic 5000

Frolic 5000

Seating

Specifications

Content	100% polyester
Weight	16.7 ± 1.0 oz./lin. yd 378 g/m ² (± 5%)
Width	54" min. useable 137 cm min. useable
Repeat	none
Backing	acrylic backcoating
Treatment	C0 stain repellent

Cleaning Code

Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup. May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners.

Miscellaneous

- Application testing of this product is recommended.
- Colors may vary between dye lots.
- This is a directional fabric.

Performance

	Colorfastness to light (AATCC 16.3 Option 3) Grade 4 min. at 40 hours
	Colorfastness to crocking (AATCC 8) Grade 4 min. dry & Grade 3 min. wet
	Breaking Strength (ASTM D5034) 250 lbf min. warp and fill
	Seam Slippage (ASTM D4034) 50 lbf min. warp and fill
	Pilling Resistance (ASTM D3511) Class 4 min.
	Flammability CA Technical Bulletin 117-2013 Section 1 EN 1021-1 Cigarette EN 1021-2 Match Flammability performance may vary depending on the substrate used.
	Abrasion (ASTM D4157) Wyzenbeek Abrasion Resistance (ASTM D4157) 100,000 double rubs min. cotton duck Martindale Abrasion Resistance (ISO 12947-2) 85,000 cycles

*Certification Marks owned by the Association for Contract Textiles, Inc.

Slate
0011

Red
0002

Cactus
0017

Blue
0004

Aubergine
0072

Pine
0007

Navy
0014

Ink
0006

duvaltex

duvaltex

USA & INTERNATIONAL | T 800-544-0200
CANADA | T 418 227-9897
For samples, visit [duvaltex.com](https://www.duvaltex.com)

